



RainBloc® for Mortar

MIXING AND DOSAGE INSTRUCTIONS

RainBloc® for Mortar from ACM Chemistries is a polymeric job site added mortar admixture that reduces or eliminates rainwater penetration through mortar without adversely affecting other properties such as bond strength and board life. It is non-corrosive and does not contain chlorides.

When used with certified water repellent concrete block made with ACM Chemistries RainBloc® Admixture, excellent water penetration resistance for the entire masonry system can be obtained. RainBloc® for Mortar also provides excellent rainwater penetration resistance in mortar used in brick masonry construction.

RainBloc® for Mortar can be used in Portland cement/lime or masonry cement mortars and is compatible with most other job-site added mortar additives

DIRECTIONS FOR USE

Add RainBloc® for Mortar and allow the mortar to mix for at least 30 seconds before adding the final water.

Note: RainBloc® for Mortar may reduce the amount of final water normally used. It is recommended to add half the amount of final water normally used and slowly add the remaining final water until desired consistency is achieved.

Mix for an additional (5) minutes after completing the final water addition to ensure the water is well mixed.

DOSAGE INSTRUCTIONS

Mortar made with Job Site Added Sand	
Portland/Lime	1.0 Qt/bag of Portland Cement (lime not included)
Masonry or Mortar Cement	0.5 Qt/bag of Masonry or Mortar Cement
Pre-Blended Mortar (with Dry Sand Included in Mix)	
Pre-Blended Bulk Mortar	0.5 Qt/3 cu.ft. of Mortar produced
Pre-Blended Bagged Mortar (80 to 100 lb/bag)	0.5 Qt/3 cu.ft. of Pre-Blended Mortar

We hope the information presented here is helpful. It is based on data considered to be true and accurate that reflects our best understanding and knowledge, and is presented for the user's consideration. We do not warrant results of actions based on any of the information contained. No statement, recommendation or suggestion is intended to infringe on any patent or copyright.